

Description

APF 4 is a high quality, quick-setting filler designed for industrial applications. It has excellent mixing and handling properties and provides exceptional adhesion with a minimal amount of shrinkage. APF 4 bonds to a wide variety of materials including wood, aluminum, cast iron, cast steel, tool steel, copper, bronze, fiberglass (FRP and SMC), honeycomb paneling and urethane foam. With its fast set time and superb machining and finishing characteristics, APF 4 is a time saver. From application to finished repair, many jobs can be completed in less than 20 minutes.

Properties

- Exceptional adhesion
- Very quick setting
- Minimal shrinkage
- Excellent finishing and machinability
- Easy to use
- Available in White, Gray and Brown

PHYSICAL PROPERTIES				
		APF 4	Cream Hardener	Mixed
Composition		Polyester Resin	BPO	
Mix ratio – by weight		100	2	
Aspect		Thixotropic paste	Thixotropic paste	Thixotropic paste
Color		White, Gray, Brown	White, Black, Red	Varies
Density at 77°F (25°C)	lbs./gal (g/cc)	13.7 (1.64)	10.0 (1.20)	13.6 (1.63)
Pot life (100 g) at 77°F (25°C)	minutes			4 – 7
Volumetric weight	lbs/in ³ (g/cc)			0.059 (1.63)

Processing Conditions

- Thoroughly blend 100 parts resin with 2 parts hardener by weight for 1 to 1 ½ minutes in a clean dry container or on a clean dry surface.
- Carefully scrape the surfaces while blending to ensure complete mixing and uniformity.

Surface Preparation and Application

- The area to be filled or repaired should be thoroughly cleaned, roughened, cleaned again and allowed to dry prior to application to ensure the best possible adhesion.
- The mixed APF 4 should be buttered into the area, avoiding trapping air during application.
- After curing to a tack-free state, the material can be sanded and finished as needed.

MECHANICAL AND THERMAL PROPERTIES			
Hardness	ASTM D-2240	Shore D	87 – 90
Tg	ASTM E-1545	°F (°C)	128 (53)
Tensile strength	ASTM D-638	psi (MPa)	2,100 (14)
Flexural strength	ASTM D-790	psi (MPa)	6,000 (41)
Compressive strength	ASTM D-695	psi (MPa)	6,200 (43)
Peak service temperature		°F (°C)	285 (141)

Storage Conditions

- Shelf life is 12 months when stored in original unopened containers between 59 – 77°F (15 – 25°C). Any opened can must be tightly closed.

Handling Precautions

Normal health and safety precautions should be observed when handling these products :

- Ensure good ventilation
- Wear gloves, and safety glasses.

For further information, please consult the material safety data sheet.

Guarantee

The information contained in this technical data sheet result from research and tests conducted in our Laboratories under precise conditions. It is the responsibility of the user to determine the suitability of AXSON products, under their own conditions before commencing with the proposed application. AXSON guarantee the conformity of their products with their specifications but cannot guarantee the compatibility of a product with any particular application. AXSON disclaim all responsibility for damage from any incident which results from the use of these products. The responsibility of AXSON is strictly limited to reimbursement or replacement of products which do not comply with the published specifications