



**P-11 TYPE I
FRP BOND & FILL
THIXOTROPIC-FLEXIBLE
LT. BROWN**



**www.axson-technologies.com
31200 Stephenson Hwy**

**800.344.7776
Madison Heights, MI 48071**

**axsonmh@axson.com
Ph 248.588.2270 Fax 248.588.5909**

DESCRIPTION

P-11 TYPE I FRP BOND & FILL, Set-Fast Filler Paste is a two-component system developed for the combined features of bonding and filling. In fiberglass-to-fiberglass, SMC-to-SMC and other applications which require non-sag (up to ½") thixotropic system with high physical properties, withstands impacts, a workable pot life of 20 minutes; which allows for quick completion of small or large projects. P-11 TYPE I accepts virtually all types of finishes with "no bleed-out" and is considered having low moisture characteristics. P-11 TYPE I has excellent heat and cold resistance and a high degree of chemical resistance. P-11 TYPE I can be applied in any desired thickness. **Typical applications include: boat decks to hulls, FRP composites to FRP, fiberglass to metal, metal to concrete, detail blocks to FRP, fiber auto panels, wood to wood, metal to metal and concrete to concrete bonding applications.**

TYPICAL HANDLING CHARACTERISTICS @ 77°F (25°C)

Mix Ratio (parts by weight or volume)	100R/2H (BPO)
Mixed Viscosity	Thixotropic Paste
Mixed Consistency	Creamy Paste
Density	1.44 g/cc
Workable Life (100 gram mass)	10-20 minutes
Finish Schedule (100 gram mass)	30 minutes
Hardness (after 1 hour)	70-80 Shore D
Shelf Life (in original unopened containers)	1 year
Storage Requirement	40°F – 80°F (4°C-27°C)

P-11 TYPE I Tech/Revised 1/20/15
Supersedes 6/16/14

The information contained in this technical data sheet results from research and tests conducted in our laboratories under precise conditions. Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. It is the responsibility of the user to determine the suitability of the Axson Technologies' products, under their own conditions, before commencing with the proposed application. In no event shall Axson Technologies, Inc. be liable for any direct, indirect, punitive, incidental, special, and/or consequential damages, to property or life, whatsoever arising out of or connected with the use or misuse of our products.

AXSON TECHNOLOGIES US +1 248 588 2270 axsonmh@axson.com axson-na.com	CHINA +86 21 58 68 30 37 marketing.china@axson.com	GERMANY +49 6 07 44 07 11-0 verkauf@axson.com	INDIA +91 20 25 56 07 10-11 info.india@axson.com	ITALY +39 02 96 70 23 36 axson@axson.it	JAPAN +81 5 64 26 25 91 sales.japan@axson.com	FRANCE Global Headquarters +33 1 34 40 34 60 axson@axson.com axson-technologies.com
	MEXICO +52 55 52 64 49 22 marketing@axson.com.mx	MIDDLE EAST +971 7 2432227 axsonmideast@axson.com	SLOVAKIA +42 1 76 42 25 26 axson.sk@axson.com	SPAIN +34 9 32 25 16 20 spain@axson.com	U.K. +44 16 38 66 00 62 sales.uk@axson.com	