

TCC-230 ADHESIVE SYSTEM TOUGHENED EPOXY ADHESIVE FOR TOOLING PLANKS



www.Axson.com 31200 Stephenson Hwy 800.344.7776

Madison Heights MI 48071

Ph 248.588.2270 Fax 248.588.5909

DESCRIPTION

TCC-230 is a two-component toughened epoxy adhesive system that was developed to be used to bond our TCC Tooling Planks together. The physical properties closely resemble our CNC Tooling Planks and it is an excellent adhesive because of its ease of use during block-up. Once cured, the **TCC-230** shows minimal glue lines. This adhesive system is well suited for our Tooling Planks that are used for ambient temperature applications.

TYPICAL HANDLING CHARACTERISTICS AND PHYSICAL PROPERTIES @ 77°F (25°C)

Mix Ratio (parts by weight) Pot Life (100 gram mass)	Resin TCC-230/Hardener TCC-102 or TCC-104	100R/17H 5 minutes
	TCC-104 Hardener	
Specific Gravity		1.06g/cc
Mixed Viscosity		4,400 cps
Mixed Color		Amber
Peak Operating Temperature		200°F (93°C)
Hardness		75 - 80 Shore D
Cure Time		12 - 24 hours
Shelf Life (in original unopened containers)	TCC-230/TCC-102 or TCC-104	2 years

SANITARY PRECAUTIONS

Do not take internally. Avoid prolonged breathing of vapors. Work in a well-ventilated area. Avoid skin contact. Protective gloves should be worn. If contact occurs: wash skin with soap and water. Avoid eye contact. If contact occurs: rinse well with water for 15 minutes, contact physician.

TCC-230 Tech/Revised 1/30/15 Supersedes 6/19/14

The information contained in this technical data sheet results from research and tests conducted in our laboratories under precise conditions. Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. It is the responsibility of the user to determine the suitability of the Axson Technologies' products, under their own conditions, before commencing with the proposed application. In no event shall Axson Technologies, Inc. be liable for any direct, indirect, punitive, incidental, special, and/or consequential damages, to property or life, whatsoever arising out of or connected with the use or misuse of our products.

+42 1 76 42 25 26

axson.sk@ax

+34 9 32 25 16 20