



**ES-224
HIGH TEMPERATURE
SURFACE COAT
ABRASION RESISTANT**



**www.axson-technologies.com
31200 Stephenson Hwy**

**800.344.7776
Madison Heights, MI 48071**

**axsonmh@axson.com
Ph 248.588.2270 Fax 248.588.5909**

DESCRIPTION

ES-224 High Temp Surface Coat is formulated for use in tooling applications where increased wear resistance in a high-temperature environment is required. The abrasion resistance of ES-224 allows for a very strong, long lasting, and durable tool surface, even under the harshest of conditions. ES-224 exhibits excellent handling characteristics and air release, creating a tool surface with a high degree of integrity and minute detail replication.

The material "B" stages in 16-20 hours at room temperature and can be cured per the recommended schedule below or pre-conditioned with intermittent usage until full properties are obtained. Use with any of the ADTECH High Temperature Laminating Systems or High Temperature Casting Systems. **Typical applications include: compression molds, oven and autoclave bonding fixtures, vacuum form molds, prototype injection molds, resin transfer molds, reactive injection molds and other applications which require elevated temperatures and abrasion resistance.**

TYPICAL HANDLING CHARACTERISTICS @ 77°F (25°C)

Mix Ratio (parts by weight)	100R/9H
Density (mixed)	14.8 lbs/gallon
Specific Gravity	1.77 g/cc
Resin Viscosity.....	74,000 cps
Hardener Viscosity.....	240 cps
Mixed Viscosity	18,500 cps
Work Life (327 gram mass)	60 minutes
Tack Free Time	2-3 hours
Demold Time	16-24 hours
Resin Color	Gray
Hardener Color	Amber
Mixed Color	Gray
Shelf Life ES-224 Resin (in original unopened container)	1 year
Shelf Life ES-224 Hardener (in original unopened container)	2 years

TYPICAL PHYSICAL PROPERTIES

Ultimate Tensile Strength (ASTM D-638.91).....	4,912psi (34MPa)
Tensile Elongation (ASTM D-638.91).....	0.143%
Ultimate Flexural Strength (ASTM D-790.92)	10,140psi (70MPa)
Flexural Modulus (ASTM D-790.92).....	680,000psi (4,688MPa)
Coefficient of Thermal Expansion by TMA (ppm/°F (°C))	23.14 x 10 ⁻⁶ in/in °F (41.65)
Heat Deflection Temperature @ 264 psi (ASTMD-648.82)	174°F (79°C)
Notched Izod Impact Strength (ASTM D-256.93A).....	8.34 in-lbs/in
Hardness (ASTM D-2240.91).....	89-91 Shore D
Glass Transition Temperature by DSC (Recommended Post Cure).....	202°F (94°C)
Glass Transition Temperature by DSC (Alternate Post Cure).....	264°F (129°C)

RECOMMENDED CURE SCHEDULE

24 hours @ 77°F (25°C)
+3 hours @ 150°F (66°C)

ALTERNATE CURE

24 hours @ 77°F (25°C)
+2 hours @ 150°F (66°C)
+2 hours @ 250°F (121°C)

Curing to a temperature 25°F (14°C) above the required service temperature is recommended.

Insure proper heat curing temperatures are met by installing a thermocouple directly in the center of the tool.

NOTE: The post cure schedule of the high-temp tooling epoxy laminate or casting system used with your surface coat would have precedence over that of the surface coat. However, to attain suitable high temperature resistance and chemical resistance, the surface coat is recommended to be post cured to a minimum of 200°F (93°C).

HEATING AND COOLING RATES DURING POST CURE

Always allow tools made with ADTECH high temperature systems to gel at room temperature before subjecting them to post cure (24 hours is usually sufficient). This will prevent excessive exotherm and shrink stress from occurring.

When oven curing laminated molds always place mold in a room temperature oven. Increase oven temperature at a rate of no more than 50°F (30°C) per hour. When heat cure is completed, turn off oven and allow molds to remain in the oven. Never remove mold from oven until mold temperature has been lowered to less than 100°F (38°C).

ES-224 Tech/Revised 1/13/15
Supersedes 5/21/14

The information contained in this technical data sheet results from research and tests conducted in our laboratories under precise conditions. Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. It is the responsibility of the user to determine the suitability of the Axson Technologies' products, under their own conditions, before commencing with the proposed application. In no event shall Axson Technologies, Inc. be liable for any direct, indirect, punitive, incidental, special, and/or consequential damages, to property or life, whatsoever arising out of or connected with the use or misuse of our products.

AXSON TECHNOLOGIES US +1 248 588 2270 axsonmh@axson.com axson-na.com	CHINA +86 21 58 68 30 37 marketing.china@axson.com MEXICO +52 55 52 64 49 22 marketing@axson.com.mx	GERMANY +49 6 07 44 07 11-0 verkauf@axson.com MIDDLE EAST +971 7 2432227 axsonmideast@axson.com	INDIA +91 20 25 56 07 10-11 info.india@axson.com SLOVAKIA +42 1 76 42 25 26 axson.sk@axson.com	ITALY +39 02 96 70 23 36 axson@axson.it SPAIN +34 9 32 25 16 20 spain@axson.com	JAPAN +81 5 64 26 25 91 sales.japan@axson.com U.K. +44 16 38 66 00 62 sales.uk@axson.com	FRANCE Global Headquarters +33 1 34 40 34 60 axson@axson.com axson-technologies.com
---	---	---	---	---	--	--