



**P-34
MODEL PLANK FILLER
CARVABLE, SEMI-RIGID
BROWN**



**www.axson-technologies.com
31200 Stephenson Hwy**

**800.344.7776
Madison Heights, MI 48071**

**axsonmh@axson.com
Ph 248.588.2270 Fax 248.588.5909**

DESCRIPTION

P-34 SET-FAST MODEL PLANK FILLER offers the pattern and model maker the capability of forming, shaping and working the cured filler to precise and accurate trade applications without dulling or damaging tools. P-34 is ideal for finishing and changing fixtures made from the new epoxy types of Model Planks (ref: TCC-1055 Model Plank). P-34 MODEL PLANK FILLER bonds to all types of wood and can be finished to a feather edge by sanding, carving, machining or scraping. P-34 is a creamy, non-sag paste which mixes easily and saves time and labor over other fillers which require longer cure. **Typical applications include as a filler/patch for: master models, engineering changes, fillets and radius areas and pattern/ fixture and tooling applications.**

TYPICAL HANDLING CHARACTERISTICS @ 77°F/25°C

Mix Ratio with BPO cream hardener (parts by weight)	100R/2H
Mixed Consistency	Smooth Creamy Paste
Working Time (100 gram mass)	4-6 minutes
Finish schedule (100 gram mass)	15-20 minutes
Cured Hardness.....	60 Shore D
Resin Color (use with White BPO cream hardener).....	Model Plank Brown
Specific Gravity	0.61 g/cc
Shelf Life (in original unopened containers)	1 year
Storage Requirement.....	40°F-80°F (4°C-27°C)

APPLICATION

P-34 MODEL PLANK FILLER can be applied with fillet balls, spatula, putty knife or any flat type tool.

P-34 Tech/Revised 1/23/15
Supersedes 6/16/14

The information contained in this technical data sheet results from research and tests conducted in our laboratories under precise conditions. Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. It is the responsibility of the user to determine the suitability of the Axson Technologies' products, under their own conditions, before commencing with the proposed application. In no event shall Axson Technologies, Inc. be liable for any direct, indirect, punitive, incidental, special, and/or consequential damages, to property or life, whatsoever arising out of or connected with the use or misuse of our products.

AXSON TECHNOLOGIES US +1 248 588 2270 axsonmh@axson.com axson-na.com	CHINA +86 21 58 68 30 37 marketing.china@axson.com	GERMANY +49 6 07 44 07 11-0 verkauf@axson.com	INDIA +91 20 25 56 07 10-11 info.india@axson.com	ITALY +39 02 96 70 23 36 axson@axson.it	JAPAN +81 5 64 26 25 91 sales.japan@axson.com	FRANCE Global Headquarters +33 1 34 40 34 60 axson@axson.com axson-technologies.com
	MEXICO +52 55 52 64 49 22 marketing@axson.com.mx	MIDDLE EAST +971 7 2432227 axsonmideast@axson.com	SLOVAKIA +42 1 76 42 25 26 axson.sk@axson.com	SPAIN +34 9 32 25 16 20 spain@axson.com	U.K. +44 16 38 66 00 62 sales.uk@axson.com	