



**PP-1052  
PATTERN PLANK®  
The Original "Red Stuff"**

**PRODUCT BULLETIN**



TOOL CHEMICAL COMPOSITES

**www.axson-technologies.com  
31200 Stephenson Hwy**

**800.344.7776  
Madison Heights, MI 48071**

**axsonmh@axson.com  
Ph 248.588.2270 Fax 248.588.5909**

**DESCRIPTION:**

**PATTERN PLANK® PP-1052** is a dense, filled urethane Tooling Plank. This plank is a light-weight, tough, cost effective alternative to metal. Its tough, high-impact resistant properties will produce dimensionally stable tools. Applications include prototype and low-volume to high volume foundry patterns, core boxes, match plates, gating and risering. Other uses include metal forming, hammer forming, stretch press dies, hemmingbucks and production checking and assembly fixtures.

**TYPICAL PHYSICAL PROPERTIES:**

	<u>U.S. Test Results</u>	<u>Metric Test Results</u>
Color.....	Red	
Hardness @ 77°F (25°C) .....	80 Shore D	
Density <sup>1</sup> .....	71 lbs/ft <sup>3</sup>	1.14 g/cc
Flexural Strength <sup>2</sup> .....	12,800 psi	88MPa
Flexural Modulus <sup>2</sup> .....	331,000 psi	2,280MPa
Tensile Strength <sup>3</sup> .....	8,900 psi	61MPa
Elongation <sup>3</sup> .....	7%	
Compressive Strength <sup>4</sup> .....	10,700 psi	74MPa
Unnotched Izod Impact (complete break) <sup>5</sup> .....	8.39 ft lbs/in	468 J/m
Heat Deflection Temperature @ 264 psi <sup>6</sup> .....	192°F	89°C
Operating Temperature @ 220°F (104°C).....	55 Shore D	
Coefficient of Thermal Expansion (ppm/°F (°C)) .....	36	64
Machinability.....	Excellent	
Stability.....	See Page 2	

**Ambient Use Adhesive System.....TCC-230 Adhesive with TCC-102 or TCC-104 Hardener**  
**Patch Paste.....TCC-52 A/B**  
**Fast Patch Paste.....TCC-5220 A/B Fast Patch Paste**

**Standard Size Available: 2", 3", 4" T x 16"W x 60"L**

**\*\*Other sizes available upon request**

Testing performed by an Independent Certified Laboratory.

- |                  |                   |                  |
|------------------|-------------------|------------------|
| 1. ASTM D 792-91 | 2. ASTM D 790-96a | 3. ASTM D 638-96 |
| 4. ASTM D 695-96 | 5. ASTM D 256-93  | 6. ASTM D 648-95 |
| 7. ASTM D 696-91 |                   |                  |

**STORAGE:** Store all Tooling Planks on a flat surface at 60°F – 100°F (16°C – 38°C).

**STABILITY OF PP-1052 PATTERN PLANK®**

	<u>Weight(g)</u>	<u>Length(mm)</u>
Initial(4" x 4" pieces)	593.81	99.69
After 24 hours at -30°F	594.00	99.40
After 24 hours at standard lab conditions	593.85	99.68
After 6 hours at 130°F	593.80	99.94
After 24 hours at standard lab conditions	593.86	99.69
After 168 hours at 100°F/100% Relative Humidity	595.74	99.75
After 24 hours at standard lab conditions	594.32	99.70
Additional 24 hours at standard lab conditions	594.31	99.70

**RECOMMENDED CNC MACHINING INFORMATION**

(Carbide Cutters are highly recommended)

	<b>Inches per minute (Feed IPM)</b>	<b>Plunge (mm)</b>	<b>Spindle Speed (rpm)</b>
2" E-Mill for Roughing	100	25	6000
3/4" Ball	75	20	3000+
1/2" Ball	60-75	10-20	3000+
1/2" x 1/32" R	40	20	4000
1/4" Ball	60	10-20	5000

These are possible recommendations. There may be some variance depending on cutters and CNC mill capabilities.

**CUTTING SUGGESTIONS FOR TOOLING PLANKS**

**CUTTING HORIZONTALLY ON A PLANNER MILL:** Head is a 10 insert, 8" in diameter. For best results use 5 inserts. Inserts are SFE-42E-10J-C5. We have found a C2 Carbide insert does not chip as easily. RPM 2200-2400 – table feed 50-55 inches per minute. Some modifications may be needed.

**SAW BLADES:** A carbide-tipped, positive rake saw blade with air slots should be used, if possible. We suggest alternate top bevel ATB or triple chip grind TCG rpm, depending on the saw. We suggest 3,500 max rpm. Check with manufacturer on saw and blade size.

- 12" blade, 48 teeth
- 16" blade, 48 teeth
- 18" blade, 60 teeth

When sawing, you may need to back part away from blade to relieve heat and binding, then proceed with cut. It may be necessary to take more than one cut to achieve best finish.

PP-1052 Tech/Revised1/28/15  
Supersedes 10/9/13

The information contained in this technical data sheet results from research and tests conducted in our laboratories under precise conditions. Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. It is the responsibility of the user to determine the suitability of the Axson Technologies' products, under their own conditions, before commencing with the proposed application. In no event shall Axson Technologies, Inc. be liable for any direct, indirect, punitive, incidental, special, and/or consequential damages, to property or life, whatsoever arising out of or connected with the use or misuse of our products.

<b>AXSON TECHNOLOGIES US</b> +1 248 588 2270 <a href="mailto:axsonmh@axson.com">axsonmh@axson.com</a> <a href="http://axson-na.com">axson-na.com</a>	<b>CHINA</b> +86 21 58 68 30 37 <a href="mailto:marketing.china@axson.com">marketing.china@axson.com</a>	<b>GERMANY</b> +49 6 07 44 07 11-0 <a href="mailto:verkauf@axson.com">verkauf@axson.com</a>	<b>INDIA</b> +91 20 25 56 07 10-11 <a href="mailto:info.india@axson.com">info.india@axson.com</a>	<b>ITALY</b> +39 02 96 70 23 36 <a href="mailto:axson@axson.it">axson@axson.it</a>	<b>JAPAN</b> +81 5 64 26 25 91 <a href="mailto:sales.japan@axson.com">sales.japan@axson.com</a>	<b>FRANCE</b> <b>Global Headquarters</b> +33 1 34 40 34 60 <a href="mailto:axson@axson.com">axson@axson.com</a> <a href="http://axson-technologies.com">axson-technologies.com</a>
	<b>MEXICO</b> +52 55 52 64 49 22 <a href="mailto:marketing@axson.com.mx">marketing@axson.com.mx</a>	<b>MIDDLE EAST</b> +971 7 2432227 <a href="mailto:axsonmideast@axson.com">axsonmideast@axson.com</a>	<b>SLOVAKIA</b> +42 1 76 42 25 26 <a href="mailto:axson.sk@axson.com">axson.sk@axson.com</a>	<b>SPAIN</b> +34 9 32 25 16 20 <a href="mailto:spain@axson.com">spain@axson.com</a>	<b>U.K.</b> +44 16 38 66 00 62 <a href="mailto:sales.uk@axson.com">sales.uk@axson.com</a>	