

## Physical Properties Bulletin

### Poly 75-Series and 77-Series Polyurethane Rubber Products

Product	Mix Ratio	Part A Color	Part B Color	Pour Time (min)	Demold Time (hr)	Total Cure Time (Days)	Specific Gravity	Mixed Viscosity (cps)	Shore A Hardness	Tensile Strength PSI (Mpa)*	% Elongation	Linear Shrinkage %	Die C Tear Strength PLI (kN/m)**
<b>Poly 75-Series</b>													
Poly 75-59	1A:1B	Clear Yellow	Clear Yellow to Amber	10	16	7	1.05	2,500	A60	637 (4.39)	588	Nil	122 (21.36)
Poly 75-60	1A:1B	Clear Yellow	Clear Yellow, Green, Blue, Amber	10	16	7	1.05	1,200	A60	545 (3.76)	459	Nil	103 (18.04)
Poly 75-65	1A:1B	Clear Yellow	Clear Yellow to Amber	35	16	7	1.04	3,000	A65	520 (3.59)	550	Nil	145 (25.44)
Poly 75-70	1A:1B	Clear Yellow	Opaque Gray	40	16	7	1.05	3,000	A70	938 (6.47)	724	Nil	299 (52.35)
Poly 75-75	2A:1B	Clear Yellow	Clear Amber	20	16	7	1.06	4,000	A75	1,064 (7.34)	722	Nil	247 (43.25)
Poly 75-79	2A:1B	Clear Yellow	Clear Yellow to Amber	20	16	7	1.07	2,000	A80	655 (4.52)	369	Nil	143 (25.04)
Poly 75-80	2A:1B	Clear Yellow	Clear Yellow to Amber	45	16	7	1.07	5,000	A80	750 (5.17)	468	Nil	199 (34.85)
Poly 75-90	2A:1B	Clear Yellow	Off-White to Tan	10-15	16	7	1.07	6,000	A90	1,979 (13.65)	774	Nil	368 (64.44)
<b>Poly 77-Series</b>													
Poly 77-50	1A:1B	Clear Yellow	Brown	15	16	7	1.07	1,500	A50	920 (6.34)	1,426	Nil	158 (27.67)
Poly 77-65	1A:1B	Clear Yellow	Brown	10	16	7	1.07	2,000	A65	1,159 (7.99)	793	Nil	180 (31.52)

<sup>1</sup>Component requires stirring before use.

\*PSI/145=Mpa (megapascals)

\*\*PLI x 0.1751 = kN/m (kilonewtons per meter)

Disclaimer: Information in this bulletin and otherwise provided by Polytek is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained by the use thereof, or that any such use will not infringe any patent. The user shall determine the suitability of the product for the intended use and assumes all risk and liability whatsoever in connection therewith.