

Physical Properties Bulletin

EasyFlo-Series Plastic Products

Product	EasyFlo 60	EasyFlo 90	EasyFlo 95	EasyFlo 100 FR	EasyFlo 120	EasyFlo Clear	EasyFlo Spray FR
Mix Ratio By Volume (By Weight)	1A:1B (100A:90B)	1A:1B (100A:90B)	1A:1B (100A:90B)	1A:1B (100A:100B)	1A:1B (100A:90B)	1A:1B (100A:85B)	1A:1B (100A:90B)
Part A Color	Clear Yellow	Clear Yellow	Clear Yellow	Clear Yellow	Clear Yellow	Clear Yellow	Clear Yellow
Part B Color	Clear Slight Yellow	Clear Slight Yellow	Clear Slight Yellow	Clear Yellow/Pink	Clear Slight Yellow	Clear Slight Yellow	Clear Yellow/Pink
Initial Mixed Viscosity, cP	60	90	95	120	120	110	250
Pot Life, min	2 - 2½	5	5	2 - 2½	2 - 2½	2 - 2½	5 seconds
Maximum Exotherm, °F (°C)	230 (110)	175 (81)	206 (97)	200 (93)	200 (93)	208 (98)	251 (122)
Demold Time (min)	15-30	30-60	30-60	15-30	15-30	15-30	5-10
Total Cure Time	7 Days	7 Days	7 Days	7 Days	7 Days	7 Days	7 Days
Linear Shrinkage	0.0041	0.002	0.0074	0.0065	0.0065	0.0154	*
Specific Gravity	1.03	1.03	1.03	1.10	1.03	1.08	1.16
Shore D Hardness	65	65	65	65	65	72	75
Tensile Strength, psi (mPA)	2,936 (20.2) 4,730 (32.6) **	3,454 (23.8) 4,080 (28.1)**	3,743 (25.8) 4,071 (28.1) **	3,170 (21.9) ND	3,534 (24.4) 5,395 (37.2) **	4,091 (28.2) ND**	7,110 (49.0)
Elastic Modulus, psi (mPA)	72,627 (500.9) 96,286 (664.0) **	60,478 (417.0) 73,507 (506.9)**	22,758 (157.0) 112,202 (773.8) **	85,928 (592.6) ND**	85,149 (587.2) 134,384 (926.8) **	97,532 (672.6) ND**	165,600 (1142.0)
Flexural Strength, 5% Strain, psi (mPA)	3,915 (27.0) 5,226 (36.0) **	4,989 (34.4) 6,338 (43.7)**	1,649 (11.4) 5,991 (41.3) **	4,284 (29.5) ND**	4,845 (33.4) 5,728 (39.5) **	6,007 (41.4) ND** ND**	10,545 (72.7)
Flexural Modulus psi (mPA)	93,112 (642.1) 127,429 (878.8) **	132,635 (914.7) 181,488 (1,251.6)**	25,072 (172.9) 32,559 (224.5) **	117,878 (812.6) ND**	133,765 (922.5) 142,940 (985.8) **	165,733 (1,143.0) ND**	280,007 (1931.1)
Heat Deflection Temperature, °F (°C)	149 (65) 167 (75) **	162 (74) 165 (76)**	132 (56) 148 (64) **	165 (74) ND**	146 (63) 159 (71) **	133 (56) ND**	175 (79)
% Elongation	13.9 9.4**	8.1 8.2**	10.1 7.1**	9.0 ND**	10.3 7.9**	7.7 ND**	8.3

¹ Component requires stirring before use.

* Shrinkage is primarily caused by gelling while hot then cooling. Parts that cure with minimal temperature rise exhibit minimal shrinkage. Reported shrinkage is inch/inch.

** Post cured for 16 hours at 160°F. If post cure data is not listed, then post cure is not recommended.

Conventions: °C = (°F -32) x 0.57

psi/145 = MPa (megaPascals)

pli x .1751 = kN/m (kiloNewtons per meter)

ND = Not Determined

Disclaimer: The information in this bulletin and otherwise provided by Polytek is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained by the use thereof, or that any such use will not infringe any patent. The user shall determine the suitability of the product for the intended use and assumes all risk and liability whatsoever in connection therewith.