

## Properties Bulletin

### FormRub Series Polyurethane Rubbers

Product	Mix Ratio	Part A Color	Part B Color	Pour Time (min)	Demold Time (hr)	Total Cure Time (Days)	Specific Gravity	Mixed Viscosity (cps)	Shore A Hardness	Tensile Strength PSI (Mpa)*	% Elongation	Linear Shrinkage % UV Resistance	Die C Tear Strength PLI (kN/m)**
<b>FormRub 35</b>	1A:1B	Clear Yellow	Turquoise	15	16	7	1.02	600	A35	283 (1.95)	2,250	Nil Fair	69 (12.08)
<b>FormRub 50</b>	1A:1B	Clear Yellow	Opaque Orange	15	16	7	1.03	800	A50	600 (4.14)	975	Nil Fair	115 (20.14)
<b>FormRub 60</b>	1A:1B	Clear Yellow	Opaque Off White to Tan	22	16	7	1.04	2,000	A60	835 (5.76)	850	Nil Poor	189 (33.09)
<b>FormRub 65</b>	1A:1B	Clear Yellow	Hazy Yellow	35	16	7	1.04	1,500	A65	500 (3.45)	600	Nil Very Good	150 (26.27)

\*PSI/145=Mpa (megapascals)

\*\*PLI x 0.1751 = kN/m (kilonewtons per meter)

Disclaimer: The information in this bulletin and otherwise provided by Polytek is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained by the use thereof, or that any such use will not infringe any patent. The user shall determine the suitability of the product for the intended use and assumes all risk and liability whatsoever in connection therewith.