

Board Material

Polyurethane Board for Styling & Design

Key Properties

- Very good surface structure
- Easily machined
- Good heat resistance
- Resistant to organic solvents

Applications

- Styling models
- Epoxy laminating molds
- Support structures
- Negative molds for casting

Mechanical Properties

| | | | SB-0240 |
|----------------------------------|-------------|--|-----------------------|
| Color | visual | | Light green |
| Density | ASTM D-792 | g/cm ³ (lb/ft ³) | ca. 0.24 (ca. 15.0) |
| Coefficient of thermal expansion | ASTM D-3386 | 10 ⁻⁶ K ⁻¹ (in/in/°F x 10 ⁻⁶) | 60 – 70 (33 – 39) |
| Deflection temperature, HDT | ASTM D-648 | °C (°F) | 55 – 65 (130 – 150) |
| Compressive strength | ASTM D-695 | MPa (psi) | 2 – 4 (290 – 580) |
| Flexural strength | ASTM D-790 | MPa (psi) | 5 – 6 (730 – 870) |

Processing

The product should have a temperature of 20°C – 25°C (68-77°F) during processing.

Packaging

| | |
|--------------------|--|
| RAKU-TOOL® SB-0240 | 96 x 24 x 4 in 96 x 24 x 8 in 96 x 48 x 2 in 96 x 48 x 4 in |
|--------------------|--|

Storage

The material should be stored flat and in a dry place. Temperature variations should be avoided during storage and transportation.



Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

For information on adhesives and repair pastes see the corresponding individual technical data sheets.